

Lugar y fecha impresión:
Aloag, 10/10/2016

Norma referencia:
NTE INEN 2167:2011

colada	ID	φ	ENSAYOS DIMENSIONALES				ENSAYOS MECANICOS					
			espac. resalt	altura resalt	ancho base resalt	α	tol masa	Fy	Fu	Fu / Fy	alargamiento	doblado
			mm	mm	mm	°	%	MPa	MPa		%	180°
			max7,0	min0,40	max3,9		+/- 6	420-540	min550	min1,25	min14	
16306693	1	10	6,45	0,52	1,15	70	2,3%	489,5	730,4	1,49	15,0	ok
16306693	2	10	6,45	0,60	1,28	70	2,4%	462,0	719,2	1,56	15,0	ok
16306693	3	10	6,45	0,50	1,21	70	0,0%	472,0	710,5	1,51	14,5	ok
16306693	4	10	6,47	0,54	1,19	70	0,0%	470,7	704,2	1,50	15,0	ok
16306693	5	10	6,47	0,52	1,20	70	-0,5%	452,0	695,5	1,54	14,0	ok
16306693	6	10	6,47	0,50	1,25	70	-1,0%	457,0	711,7	1,56	16,0	ok
16306693	7	10	6,51	0,49	1,23	70	-0,1%	477,0	709,2	1,49	15,5	ok
16306693	x	10	6,5	0,52	1,2	70	0,5%	468,6	711,5	1,52	15,0	ok
colada: 126ton		max	6,5	0,60	1,3	70	2,4%	489	730	1,56	16,0	
		min	6,4	0,49	1,2	70	-1,0%	452	695	1,49	14,0	

Method: Fe-10-F
Comment: Aceros Baja Aleacion Type corr.concentr.
Type Standard SAE-1026 NUEVO

9/29/2016 1:39:07 PM

ASTM: **E415** Quality: **ANALISIS COMPROBACION** Sample: **16306693**

	C	Si	Mn	P	S	Cu	Cr	Ni
	%	%	%	%	%	%	%	%
min								
< x > (7)	0.308	0.163	0.851	0.0205	0.0346	0.446	0.113	0.110
max	0.330	0.550	1.560	0.0430	0.0530			

	Mo	Al	V	B	Fe	C.E.		
	%	%	%	%	%			
min								
< x > (7)	0.021	0.0026	0.036	< 0.0002	97.82	0.474		
max								